

## **TECHNICAL DATA SHEET**

## 10th Generation Smart Tint®

CONFIDENT	Non-Adhesive		Smart Cling® Self-Adhesive  Low driving voltage	
	(HC-NF)	High on clarity (LV-NF)	(HC-SF)	High on clarity (LV-SF)
FILM THICKNESS	1 Mil		1 Mil	
FILM SIZES	71" x 1958" or 1800mm x 50m		71" x 1958" or 1800mm x 50m	
UV BLOCK	> 99 %		> 99 %	
IR BLOCK	Standard Low Haze High Clarity > 20 %	IR90 Low Haze Clarity + Heat Block	Standard Low Haze High Clarity > 20 %	IR90 Low Haze Clarity + Heat Block > 98 %
SOLAR HEAT GAIN COEFFICIENT (950 nm)	0.71	0.1	0.71	0.1
OPERATION TEMPERATURE	-10° C ~ 60° C			
PARALLEL LIGHT TRANSMITTANCE (650 nm)	96±1 (on) 1.8±0.5 (off)	98±1 (on) 2±1 (off)	96±1 (on) 1.8±0.5 (off)	98±1 (on) 2±1 (off)
TOTAL LIGHT TRANSMITTANCE	90±1 (on) 4±2 (off)	98±1 (on) 4±2 (off)	90 ±1 (on) 4 ±2 (off)	98±1 (on) 4±2 (off)
HAZE	3±1 (on) 89±2 (off)	3±1 (on) 98±1 (off)	3±1 (on) 89±2 (off)	3±1 (on) 98±1 (off)
OPERATING VOLTAGE	28 ~ 60 VAC	28 ~ 60 VAC	28 ~ 60 VAC	28 ~ 60 VAC
FREQUENCY RANGE	50 ~ 60 Hz			
POWER CONSUMPTION	3 ~ 4 W/m²			
SWITCHING SPEED	Off → On: 50	~ 100 milliseconds /	/ On $\rightarrow$ Off: 200 ~ 3	00 milliseconds

\*HC = USA/CANADA Line Voltage / LV = Low Voltage

Tinsel Strength Tested - 14,000 lbs. per square inch



Look for the serial # on every piece of Smart Tint®